

Featureflor

Packaging



Mixing



Application



Uses



Substrates

Concrete floors,
Terrazzo and
ceramic tiles

Smooth, polishable, self-levelling, decorative flooring compound

Description

A white resin modified, fast setting, chemical cure, cement based compound used as a decorative flooring screed. Its smooth consistency and high fluidity allow ease of placement, trowelling and finish.

Uses

Use internally and apply to properly prepared concrete, terrazzo and ceramic tiles to form an economical, white, decorative flooring surface. When applied by an experienced applicator, the addition of clean marble aggregate, oxide and water-based pigments can be ground and polished to achieve a terrazzo-like appearance. Use to achieve a wear and impact resistant floor in shops, hotels, cafes, exhibition areas and residential applications.

Features

- Durable and crack resistant (exceeds 40MPa)
- Self-levelling
- Rapid set - 2-4 hours
- Smooth finish
- For thickness 5-50mm
- Wear and impact resistant
- White can be coloured or modified with marble aggregate
- Decorative

Performance Data

	1 day	7 days	28 days
Compression Strength	14.0MPa	32.0MPa	40.0MPa
Flexural Strength	5.0MPa	6.0MPa	7.0MPa
Adhesion to substrate	1.0MPa		

Coverage (Approximate)

1.5kg/m² per 1mm thickness.

Specification

Featureflor shall be a self-levelling, decorative, fast curing compound with a minimum compression strength of 40MPa manufactured by **Construction Chemicals** and shall be applied in accordance with the manufacturer's application instructions.

Surface Preparation

Surfaces must be firm and structurally sound, free from dirt, wax, oil, grease, paint, ponded water, laitance and all contaminants. Contaminated/ultra smooth floors will need to be mechanically abraded or dustless shot-blasted to roughen and abrade the surface before priming. When in doubt about the surface preparation or priming, a 1m² test area is recommended. A thorough repeated sweeping with a hard broom, followed by mopping with clean water to remove all contaminants is essential before priming.

Priming

To prevent rising of air bubbles and to improve adhesion of the applied surface, the substrate must be completely covered with primer.

Porous concrete: Prime with **Super Prime** applied with a hard broom or brush to penetrate into the substrate (may require 2 coats).

Helicopter or steel trowelled finish concrete, terrazzo, ceramic tile or non-porous surfaces: Prime with **Primax** applied with a hard broom or brush, working well into the surface.

Damp concrete/difficult to adhere to substrates: Apply **Epecrete** with a brush to dampproof the floor and improve adhesion.

Mixing

Featureflor is to be applied by experienced levelling applicators. Mix ratio is 4 litres of water (exactly) to 20kg of **Featureflor**. Mix 3-6 bags using a 'Hippo' or similar mixer, using a 2-3 man team to mix and apply. Use a spiked roller to remove air bubbles and blend mixes together. Mix for 1-2 minutes and place the product immediately - the levelling properties reduce in effectiveness after 10 minutes making levelling and finishing more difficult. Use the mixture within 15 minutes. Discard unused material after this time.

Featureflor can be applied 5-50mm thickness. Over 30mm for economy, add 1 part of mixed **Featureflor** to 1 part 3-8mm washed aggregate while mixing mechanically.

- Can be mixed with up to 5% oxide to obtain the desired colour.
- Marble aggregate can be added and polished to obtain a terrazzo appearance.

Pot life at 20°C is approximately 30 minutes and is walkable after 3 hours but will vary on temperature.

Application

Pour the mixed **Featureflor** onto the prepared floor and spread with a levelling compound spreader or large metal trowel, keeping the trowel slightly inclined to obtain the desired thickness. Spread the material to the desired thickness in one application. Use sufficient material to cover high points with 2-3mm thickness. **Featureflor** smooths itself during the first 10 minutes. Apply when the temperature is 5-30°C, do not apply in direct sunlight as this can cause the surface to crack. If required, an additional layer or finish coat over an aggregate mix can be applied after the surface is primed with **Primax** but the layer should not exceed 50% of the previous layer. **Featureflor** can be walked on in 2-4 hours and put into use the next day, 15 hours @ 23°C @ 50% relative humidity.

Sealing

The floor can be coated when the surface is dry with **Durathane**.

Precautions

Do not hand mix or add in excess of 4.0 litres of water as this causes lumps, cracking, reduced strength and bond failure. A whitish/yellow layer on the surface indicates over watering. Do not apply externally or on permanently damp surfaces.

When polished, natural effects become visible, i.e., water and trowel marks, and random spotting. Protect the surface from damage until it has sufficient strength with 3mm MDF to avoid mechanical damage. Sweep and vacuum repeatedly to preserve the surface.

Non-toxic but contains cement which contains silica. Wear gloves and appropriate respirator. Further information for this product is contained in the Material Safety Data Sheet. Refer; www.constructionchemicals.com.au

Shelf Life

1 year



Adelaide Phone (08) 8243 7888

Darwin Phone (08) 8947 1811

Perth Phone (08) 9356 9999

Auckland Phone (09) 273 5444

Brisbane Phone (07) 3271 2944

Melbourne Phone (03) 9761 4711

Sydney Phone (02) 9756 3533

Kuala Lumpur Phone (603) 5122 2522

www.constructionchemicals.com.au

The information contained in this technical publication is based on our current knowledge and experience and is provided as a guide only. In view of the many factors that may affect application it is the user's sole responsibility to ensure suitability for a specific purpose.