

Acoustibond

Packaging




Mixing



Application



Uses



Substrates

- Floors
- Concrete
- Cement Screed
- Compressed Cement
- Sheeting

Two-pack ceramic tile adhesive with soundproofing properties

Description

Acoustibond is a two-pack acrylic/cement based ceramic tile adhesive with soundproofing properties.

Features

- Easy mixing – two-pack formulation based on an acrylic resin and a cement / rubber crumb based powder
- Easy application – trowelable viscosity
- Low odour
- Water resistant
- Low V.O.C.
- Excellent adhesion to building surfaces
- Flexible
- Enhances acoustic and thermal properties
- Reduce impact noise by half (up to 8 decibels)

Uses

A two-pack acrylic/cement based ceramic tile adhesive for bonding ceramic tiles to concrete, cement sheet and structural timber.

Performance data

Exceeds the performance requirements of AS ISO 13007.1-2013.

Tensile Adhesion Strength

1.02MPa

Precautions

Do not alter mix ratio in any way (mixing extra powder or water), as this will substantially reduce its acoustic and adhesive properties. Not recommended for use with mosaic tiles. We recommend **Acoustiflor**.

Coverage (Approximate)

25kg powder plus 20L liquid / 12-14m² using 12mm notched trowel, over a true surface to give a minimum 3mm dry adhesive bed thickness.

Specification

The ceramic tile adhesive will be an acrylic/cement two-pack system such as **Acoustibond** manufactured by **Construction Chemicals** and shall be applied in accordance with the manufacturer's application instructions. It shall exceed the acoustic requirements of the Building Code of Australia.

Surface preparation

All surfaces must be firm and clean, free from dust, waxes, paint, laitance and all contaminants.

Priming

When applying **Acoustibond** directly to structural timber, porous concrete, cement screed and cement sheeting, prime with **Primebond**.

Impact noise test results				
Noise reduction	FIIC	200mm concrete slab with 13mm suspended ceiling with 150mm ceiling cavity (with no insulation)	L'nT,w Decibels (dB)	Noise reduction
	43	Bare Floor	56dB	Changes in sound level 3dB=Clearly noticeable 10dB=Half as loud
13	56	3mm Acoustibond 300mm x 300mm ceramic tiles	48dB	8dB

FIIC (Field Impact Isolation Class) The higher the number the better the result						L'nT,w (Measured in decibels) The lower the rating the better the result					
FIIC	40	45	50	55	60	Star rating	2	3	4	5	6
Performance	Not acceptable	Poor	Acceptable	Good	Excellent	Performance (dB)	65	55	50	45	40

Acoustibond exceeds the acoustic requirements of the Building Code of Australia.

The FIIC and L'nT,w rating vary depending on the building construction (i.e. concrete thickness, strength, use of suspended ceilings, density of tile/stone, and installation details). An accurate test is recommended for specific site performance figures.

Mixing

Mix 5 litres of liquid with 6kg powder to a thick creamy consistency. Pot life is approximately 1 hour, depending on temperature. Allow to stand for 5-10 minutes and restir before use.

Application

Apply adhesive with a 12mm notched trowel applying only 1 square metre at a time. (**Do not** spot fix tiles). Fix tiles while the adhesive is wet on the surface. Press the tiles firmly into the adhesive ridges so that there are no voids beneath the tiles. Do not presoak tiles. Clean excess adhesive from the tile and grout joint before it dries. The adhesive bed must be not less than 3mm.

When using **Acoustibond** tiles must be separated from the walls with 6mm polyethylene foam tape.

Cleaning up

Uncured **Acoustibond** may be removed from tools and equipment with water. Once cured, the material can be removed with any strong solvent.

Cure time

The floor can be grouted after 24 hours @ 23°C 50% relative humidity.

Safety precautions

Non-toxic but contains cement which contains silica. Wear gloves and appropriate respirator. Further information for this product is contained in the Material Safety Data Sheet. Refer; www.constructionchemicals.com.au

Shelf life

1 year powder / 2 years liquid.



Adelaide Phone (08) 8243 7888

Darwin Phone (08) 8947 1811

Perth Phone (08) 9356 9999

Auckland Phone (09) 273 5444

Brisbane Phone (07) 3271 2944

Melbourne Phone (03) 9761 4711

Sydney Phone (02) 9756 3533

Kuala Lumpur Phone (603) 5122 2522

www.constructionchemicals.com.au

The information contained in this technical publication is based on our current knowledge and experience and is provided as a guide only. In view of the many factors that may affect application it is the user's sole responsibility to ensure suitability for a specific purpose.