


**Dribond**

# Kemgrip Floor & Wall

## Packaging



## Mixing



## Application



## Uses



## Substrates

Concrete  
Brick  
Block  
Cement Render

## Waterproof ceramic tile adhesive with extra bond

### Description

**Kemgrip Floor & Wall** is a cement powder based adhesive formulated to be mixed with water. A thick or thin bed adhesive for bedding and fixing ceramic tiles to firm masonry surfaces.

### Features

- Exceeds the requirements of AS4992
- Waterproof
- Extra bond

### Coverage (Approximate)

3-6m<sup>2</sup> per 20kg, depending on tile size and trowel notch size.

### Performance data

Exceeds the performance requirements of AS4992.

### Tensile Adhesion Strength

1.9MPa (28 days)

### Specification

The ceramic tile adhesive will be a waterproof cement based adhesive that conforms to AS4992 and has a minimum tensile adhesion strength of 1.9MPa such as **Kemgrip Floor & Wall** manufactured by Construction Chemicals and shall be applied in accordance with the manufacturer's application instructions.

### Surface preparation

The surface to be tiled must be firm and clean, free from dust, waxes, paint and other contaminants. Steel floated concrete floors must be mechanically roughened, washed thoroughly and allowed to dry prior to tiling. Prime with **Primax** on external and smooth surfaces and **Primebond** on internal porous surfaces. **Kemgrip Floor & Wall** will adhere most tiles, however when fixing vitrified or non-porous tiles, additional bond is required by adding 1 litre of **Kemcrete** to 20kg of **Kemgrip Floor & Wall**.

### A guide to tile joint sizes

Internal minimum 2mm, external minimum 4mm or as specified by the tile manufacturer and AS3958.1-2007. **Do not** fix tiles with tight joints.

When grouting joints of less than 3mm we recommend mixing the grout with **Primebond**. Greater care is needed to place the grout deep into joints before pointing the joints to compact the grout surface.

### Swimming pools

Prime surface with **Primax**, add **Elastacrete** in place of water to **Kemgrip Floor & Wall**. Tile in cool conditions. Grout with **Kemgrout Sanded** mixed with **Primebond**. Allow to cure for 21 days @ 23°C – 50% relative humidity.

### Mixing

Mix with clean water using 2-3 litres to 10kg. Add the powder to the water while mixing with a slow speed electric drill to obtain a lump-free creamy consistency.

### Application

Apply with a notched trowel. For tiles 400mmx400mm or greater use a 12mm notch and buttered tile back (as per the Australian Standard AS3958.1-2007). The final bed thickness must not be less than 2mm for walls and 3mm for floors, to accommodate movement. Spread about 1 metre at a time. Tiles must be set in place while the adhesive is still wet on the surface. Press tiles firmly into the adhesive using a slight twisting motion. Tiles must be firmly bedded into the adhesive so no voids occur beneath the tiles. **Do not** spot fix.

### Grouting

Grouting should be commenced after 24 hours and is trafficable after 3 days. Grout with **Kemgrout**.

### Safety precautions

Non-toxic but contains cement which contains silica. Wear gloves and appropriate respirator. Further information for this product is contained in the Material Safety Data Sheet. Refer; [www.constructionchemicals.com.au](http://www.constructionchemicals.com.au)

### Shelf life

1 year.

**CONSTRUCTION CHEMICALS**

**Adelaide** Phone (08) 8243 7888

**Darwin** Phone (08) 8947 1811

**Perth** Phone (08) 9356 9999

**Auckland** Phone (09) 273 5444

**Brisbane** Phone (07) 3271 2944

**Melbourne** Phone (03) 9761 4711

**Sydney** Phone (02) 9756 3533

**Kuala Lumpur** Phone (603) 5122 2522

[www.constructionchemicals.com.au](http://www.constructionchemicals.com.au)

The information contained in this technical publication is based on our current knowledge and experience and is provided as a guide only. In view of the many factors that may affect application it is the user's sole responsibility to ensure suitability for a specific purpose.

051 Nov 11