

**Dribond**

# Kemgrout Flexible

## Waterproof tile grout – mould and fungi resistant

### Packaging



### Mixing



### Application



### Uses



Floor



Wall

### Substrates

ceramic tile  
mosaics  
marble  
natural stone  
porcelain

### Description

A dense, smooth, hard-wearing, flexible polymer modified portland cement floor and wall grouting compound with resistance to mould and fungi growth for joints up to 5mm wide.

### Uses

A smooth, hard-wearing grout formulated for interior, exterior, wet area floor and wall grouting applications.

### Features

- Easy to use and clean
- Dense, Flexible and Hard-wearing
- Colour match tiles
- Mould and Fungi Resistant

### Coverage (approximate)

Wall Tiles 0.5 kg/m<sup>2</sup>  
Mosaics 1.0 kg/m<sup>2</sup>  
over 3mm joints 1-2 kg/m<sup>2</sup>

### Performance Data

**Compression Strength** (ASTM C109) 35MPa

**Moisture Absorption** (ASTM C413) 5%

### Specification

The grout shall be a flexible polymer modified waterproof tile grout with a minimum compression strength of 35MPa such as **Kemgrout Flexible** manufactured by Construction Chemicals and shall be applied in accordance with the manufacturer's application instructions.

### A guide to tile joint sizes

Internal minimum 2mm, external minimum 4mm or as specified by the tile manufacturer and AS3958.1-2007. **Do not** fix tiles with tight joints. When grouting joints of less than 3mm we recommend mixing the grout with **Primebond**. Greater care is needed to place the grout deep into joints before pointing the joints to compact the grout surface.

### Mixing

Mix grout to a thick, uniform, creamy mixture by adding powder to clean water - Ratio of approx. 0.5 litres of water to 2 kg of powder. Do not over mix, or add excessive water as shrinkage cracks may result. Allow to stand 5-10 minutes then restir before use.

### Application

Grout tiles after the adhesive has had sufficient time to set – 24 hours for walls and 48 hours for floors. Dampen the tile joint with a sponge and apply the prepared grout, spreading 3m<sup>2</sup> at a time, working well into the joints with a sponge, grouting tool or piece of rubber. Point joints with the edge of a grouting tool or piece of rubber to pack grout firmly into place. Remove surplus grout with a damp cloth or sponge. Do not allow the grout to harden on the face of the tiles. When a haze forms over the tiles, polish carefully with a dry cloth and remove haze completely.

- Allow grout to cure for 24 hours @ 23°C, 50% relative humidity

Mix grout with **Primebond** to increase resistance to staining and discolouration. Changes the colour of the grout to the next darker shade.

### Precaution

Colour shade variations can occur due to tile porosity, variations, finishing techniques and site conditions. Cracking and colour variations can occur if excessive water is used in mixing or clean-up. Water must be uncontaminated/potable. Do not use **Kemgrout Flexible** in expansion/movement joints, use **Colour Seal**. Prior to grouting, remove waxes and release agents from the tile surface to prevent grout discolouration. Swimming pools use **Kemgrout Sanded**.

### Safety Precautions

Non-toxic but contains cement which contains silica. Wear gloves and appropriate respirator. Further information for this product is contained in the Material Safety Data Sheet. Refer; [www.constructionchemicals.com.au](http://www.constructionchemicals.com.au).

**Shelf Life** 1 year.

**CONSTRUCTION  
CHEMICALS**

[www.constructionchemicals.com.au](http://www.constructionchemicals.com.au)

● **ADELAIDE** PH: (08) 8243 7888

● **DARWIN** PH: (08) 89471811

● **PERTH** PH: (08) 9356 9999

● **AUCKLAND** PH: (09) 273 5444

● **BRISBANE** PH: (07) 3271 2944

● **MELBOURNE** PH: (03) 9761 4711

● **SYDNEY** PH: (02) 9756 3533

● **KUALA LUMPUR** PH: (603) 5122 2522