

Dribond

Mosaicbond

Packaging




Mixing



Application



Uses



Substrates

Gypsum
Plasterboard
Cement sheet
Concrete,
brick, block
Cement render

A flexible, glass mosaic adhesive/grout

Description

Mosaicbond is a premium grade, internal and external floor and wall adhesive with exceptional performance. **Mosaicbond** is formulated to allow the bonding and grouting (1.5mm-3mm joints) of mosaics tiles in one application. Can be used on many different surfaces ie. fibre cement sheet, plasterboard, concrete, ceramic tiles and smooth concrete.

Uses

A thin bed internal and external floor and wall adhesive for fixing and grouting mosaic tiles over most substrates eg: cement render, fibre cement sheets, plasterboard, existing properly prepared ceramic tiles and Construction Chemicals waterproof membranes.

Features

- Exceptional adhesion – suitable over a number of difficult to bond substrates.
- Waterproof – ideal for water features and full immersion.
- Flexible – accommodates normal building movement.
- White (ideal for glass mosaics) and colours available.
- High initial adhesion – reduces the need for support in wall tiling applications.
- Allows tiling and grouting of mosaics in one process.

Coverage (Approximate)

Mosaicbond can be mixed with **Flexible** or **Sanded Grout**. 1L **Mosaicbond** with 2.4kg **Kemgrout Flexible**. 1L **Mosaicbond** with 3.6kg **Kemgrout Sanded** and will cover approximately 1.0-1.2m² depending on grout joint width and bed thickness.

Surface preparation

The surface to be tiled must be structurally sound and clean, free from laitance, release agents, curing compounds, dust, waxes, paint and all contaminants. Prime porous substrates, cement sheet, building boards and up to 32MPa concrete with **Primebond**. New concrete must be 28 days old. Immersed, damp and non porous ie. swimming pool. Must be primed with **Primax**. When using glass mosaics in fully immersed conditions check with the tile supplier as to the suitability (the adhesive used to fix the mesh to the back of the mosaic may swell

and breakdown under these conditions). Ensure that no more than 10% of the back of the sheet of mesh mounted mosaic is covered by the substance used to adhere the glass mosaic to the mesh.

A guide to tile joint sizes

Internal minimum 2mm, external minimum 4mm or as specified by the tile manufacturer and AS3958.1-2007. **Do not** fix tiles with tight joints. When grouting joints of less than 3mm we recommend mixing the grout with **Primebond**. Greater care is needed to place the grout deep into joints before pointing the joints to compact the grout surface.

Mixing

Mix 1L of **Mosaicbond** with approximately 2.4kg of **Kemgrout Flexible** or 3.6kg of **Kemgrout Sanded** to a thick creamy consistency. (Adjust mix to suit users preference) Pot life is approximately 1-2 hours @ 23°C @ 50RH.

Set time

Approximately 24 hours, depending on temperature, humidity and substrate porosity. Allow longer for dense tiles. Swimming pools allow 4 weeks before filling pool.

Application adhesive & grout

Apply the adhesive using one of the following methods.

1. Using a 6mm x 6mm notched trowel apply mixed **Mosaicbond** to the substrate. Place the mosaic sheet face down and fill the grout joints by buttering the back of the tile. Place the mosaic sheet and bed onto the surface using a flat wooden sheet (that is slightly larger than the mosaic sheet) to level the sheet. Clean up excess adhesive and repeat with following sheets.
2. Using a 10mm x 10mm notched trowel apply the mixed **Mosaicbond** to the substrate. Place the mosaics onto the adhesive forcing adhesive into the grout joints then top up grout with a rubber grouter until filled and flush. Clean up excess adhesive and repeat with the following sheets.

The final bed thickness must not be less than 2mm for walls and 3mm for floors, to accommodate movement. Spread 1m² at a time;

do not allow the adhesive to 'skin', bed the tiles while the adhesive is still wet on the surface. Press mosaics firmly into the adhesive ensuring full bedding of the mosaics. Allow the adhesive to come up between the grout joints so grouting can be done at the same time, use more adhesive if required to grout as tiling is being done. Clean adhesive off the tile face before adhesive dries.

Swimming pools

We recommend the use of **Kemgrout Sanded** mixed with **Primebond**, as a grout in swimming pools because of its chemical resistance and its more colour fast in a chemically aggressive situations.

Grouting

Remove surplus grout with a damp cloth or sponge. Do not allow the **Mosaicbond** to harden on the face of the tiles. When a haze forms over the tile polish carefully with a dry cloth. **Pin holes and imperfections in the grout can be corrected by a finish application of grout.**

Safety precautions

Non-toxic but contains cement which contains silica. Wear gloves and appropriate respirator. Further information for this product is contained in the Material Safety Data Sheet. Refer; www.constructionchemicals.com.au

Shelf life

1 year. Store in a cool dry place out of direct sunlight.



Adelaide Phone (08) 8243 7888

Darwin Phone (08) 8947 1811

Perth Phone (08) 9356 9999

Auckland Phone (09) 273 5444

Brisbane Phone (07) 3271 2944

Melbourne Phone (03) 9761 4711

Sydney Phone (02) 9756 3533

Kuala Lumpur Phone (603) 5122 2522

www.constructionchemicals.com.au

The information contained in this technical publication is based on our current knowledge and experience and is provided as a guide only. In view of the many factors that may affect application it is the user's sole responsibility to ensure suitability for a specific purpose.