

Reinforced Screed

IMPACT RESISTANT FLOORING COMPOUND

PACKAGING




MIXING



APPLICATION



USES



SUBSTRATES

CONCRETE FLOORS

DESCRIPTION

REINFORCED SCREED is a premixed fast setting cement based resin modified screed. Blended with alkali resistant glass fibres and hard wearing aggregates to make a hardwearing impact, crack and chemical resistant floor repair compound.

USES

REINFORCED SCREED is formulated for repair work where abrasion, chemical, temperature and crack resistance are required and where the need to place the surface back into service quickly is essential. REINFORCED SCREED is suitable as a patching and resurfacing material for concrete roads, industrial and factory floors and dairy and piggery floors.

FEATURES

- Strong, durable, crack resistant.
- Self levelling properties.
- Can be feather edged.
- Aggregate can be added when using over 5 mm thick.
- Water resistant.
- Fast setting allows use within 6 hours of application.
- Chemical resistant – from pH 4 to 12.
- Temperature resistant – from -100° to 1,200°C.
- Wear resistant – three times harder than concrete.

COVERAGE (Approximate)

3mm thick – 5 kg/m². 5mm thick – 8 kg/m².

PERFORMANCE DATA

	1 Day	7 Day	28 Days
Compression Strength (BS4551) Mpa	28.3	62.7	79.3
Flexural Strength (BS4551) Mpa	5.64	9.94	12.43
Hardness (Brinell)	30	52	54

SPECIFICATION

The flooring compound shall be a glass fibre reinforced cement compound with a minimum compression strength of 79 Mpa such as REINFORCED SCREED manufactured by Construction Chemicals and shall be applied in accordance with the manufacturers instructions.

SURFACE PREPARATION

Surfaces must be firm and free from dirt, wax, oil, grease, paint and other contaminants.

Smooth and contaminated surfaces must be mechanically roughened then wash thoroughly with large quantities of water.

Wax and grease must be removed with industrial detergent.

Porous surfaces must be either well dampened with water (several applications to ensure complete saturation may be necessary) or prime surfaces with a 50:50 water: BONDING ADDITIVE solution. A thorough repeated sweeping with a hard broom to remove dust and dirt before applying primer or REINFORCED SCREED is essential.

When in doubt about the substrate preparation a test patch is recommended to test adhesion.

MIXING

Place 2 litres of water and 2 litres BONDING ADDITIVE in a mixing container, mix together and gradually add, by sprinkling, the 20 kg of REINFORCED SCREED while stirring continuously. Mix until all lumps have dissolved and a thick creamy consistency is obtained. Use the mixture within 30 minutes – do not add water to retemper mix – discard unused mix after 30 minutes. For layers over 5mm add a course sharp aggregate to the mix material, e.g., granite chip, coarse river sand. Add up to 1/3 coarse filler to 2/3 REINFORCED SCREED.

APPLICATION

Pour the mixed screed on to the prepared floor and with a steel trowel at a sharp angle, force the mixture into the original concrete, then holding the trowel normally, flat spread the material to the desired finish in one application. Apply the screed when the temperature range is 5°-30°C and do not apply in direct sunlight or in hot weather conditions.

CURING

Normally curing is not necessary, but when applying thin coats, i.e. under 4 mm thick and when the surface is exposed to direct sunlight, warm atmosphere or low humidity conditions, the surface must be kept moist or covered with an impermeable membrane for up to 24 hours as soon as the surface can be walked on.

STORAGE

Store off the ground in dry cool environment.

SHELF LIFE

1 year



ADELAIDE 467 - 469 SOUTH RD REGENCY PARK 5010 PH: (08) 8346 8013 FAX: (08) 8340 2052

BRISBANE 45 COULSON ST WACOL 4076 PH: (07) 3271 2944 FAX: (07) 3271 3892

MELBOURNE 11 GABRIELLE CT BAYSWATER NORTH 3153 PH: (03) 9761 4711 FAX: (03) 9761 4748

PERTH 11 COLLIE RD WELSHPOOL 6106 PH: (08) 9356 9999 FAX: (08) 9356 9955

SYDNEY 31 NEWTON RD WETHERILL PARK 2164 PH: (02) 9756 3533 FAX: (02) 9756 3534

AUCKLAND 16 CARPENTER RD EAST TAMAKI PH: (09) 273 5444 FAX: 0800 266 236

KUALA LUMPUR LOT 2 JALAN KECAPI 33/2 ELITE INDUSTRIAL ESTATE OFF JALAN BUKIT KEMUNING
40000 SHAH ALAM PH: (603) 5122 2522 FAX: (603) 5122 2526